



Exclusively Distributed by:

 PPG Protective & Marine Coatings
Bringing innovation to the surface.™

PlexiDeck MMA Primer

Primer for MMA Systems

Product Data

Description

Plexicoat America PlexiDeck MMA Primer is a methyl-Methacrylate primer for use within the Plexicoat America Floor System. PlexiDeck MMA Primer is a solvent free, 2-component, 100% reactive, medium viscosity primer. PlexiDeck MMA Primer has superior adhesion to concrete and is ideal as a primer or sealer for porous concrete surfaces. PlexiDeck MMA Primer should completely seal the concrete surface resulting in a uniform satin finish. PlexiDeck MMA Bond Promoter can be utilized with the PlexiDeck MMA Primer as suitable primer for metal and tile substrate applications.

Yield

All coverage rates are approximate. Coverage rates will vary with the desired texture and porosity of substrate. Typically, a batch of PlexiDeck MMA Primer will achieve a coverage rate of 100 square feet. See mixing chart.

Packaging

4.5 gallon pail
49 gallon drum

Color

Clear, slightly turbid

Shelf Life

One year when properly stored

Features

- Fully cures in one hour
- Great adhesion to concrete
- Can be applied at -20°F (-29°C)
- Primer for concrete, wood and tile applications
- Can be used as one coat sealer over concrete

Benefits

- Reduction in downtime and rapid return to service
- Ideal for porous concrete surfaces
- Suitable for incidental food contact (R2)
- Can perform installations in cold temperatures
- Metal Primer Formulation Available

Where to Use

Used as a primer within the following Plexicoat America Flooring Systems:

- All PlexiDeck MMA Systems
- Use PlexiDeck Metal Primer ST over metal needing rust inhibitive and corrosion inhibitive properties

Please refer to the PlexiDeck Installation Guide or individual PlexiDeck Systems data sheets for application instructions.

Every Plexicoat America Flooring Systems is a multiple component system that utilizes a methyl methacrylate (MMA) resin. It is critical that the instructions listed in the Material Safety Data Sheet and on the product label for every component of the system be read, understood and followed. MMA resins are flammable liquids in their uncured state.

Smoking, open flames or sparks should not be permitted during the handling of the product.

Explosion safe ventilation must be used during the application to minimize vapor collection in the installation area and to improve overall air quality for the crew. All foodstuffs must be removed during installation of the flooring system.

Physical Data

Color	Clear, slightly turbid
Components	One plus PlexiDeck MMA Powder Hardener
Recommended Thickness	10 – 12 mils
Coats	One
VOC	None

Application Data

Applied over	concrete, wood and tile
Primer	self priming
Method	Brush, roll or squeegee
Pot Life	7 – 15 minutes
Min Recoat	30 – 60 minutes
Max Recoat	none
Cure Time	60 minutes (full cure)
Temperature	-20°F – 104°F See mixing chart
Clean Up	PlexiDeck MMA Prep Cleaner

Typical Properties after 60 minutes

Percentage of Reative Resin	100%
Water Absorbtion (%24 hours) (ASTM D570)	<0.1%
Tensile Strength (ASTM D638)	4,250 psi
Elongation @ Break (ASTM D638)	3%
Hardness (Shore D) (ASTM D2240)	83
Viscosity (ASTM D2392)	220-300 cps

Bond Test

A bond test should be conducted to determine the adequacy of the surface preparation and the bond to substrate before proceeding with the application of the primer to the entire area. The bond of the primer to the substrate should be greater than the tensile strength of the substrate itself (adhesive bond of PlexiDeck System to concrete should be stronger than cohesive bond of concrete itself); therefore, there should be fractured aggregate along the entire patty. If only a fine laitance or small amount of concrete is attached, additional mechanical preparation is required. The exact procedure for performing the bond test can be found in the sheet titled "The Bond Test," provided by Plexicoat America, LLC.

For professional use only. Not for sale to or use by the general public.

LIMITED WARRANTY NOTICE Every reasonable effort is made to apply PLEXICOAT AMERICA exacting standards both in the manufacture of our products and in the information which we issue concerning these products and their use. We warrant our products to be of good quality and will replace or, at our election, refund the purchase price of any products proved defective. Satisfactory results depend not only upon quality products, but also upon many factors beyond our control. Therefore, except for such replacement or refund, PLEXICOAT AMERICA MAKES NO WARRANTY OR GUARANTEE, EXPRESS OR IMPLIED, INCLUDING WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY, RESPECTING ITS PRODUCTS, and PLEXICOAT AMERICA shall have no other liability with respect thereto. Any claim regarding product defect must be received in writing within one (1) year from the date of shipment. No claim will be considered without such written notice or after the specified time interval. User shall determine the suitability of the products for the intended use and assume all risks and liability in connection therewith. Any authorized change in the printed recommendations concerning the use of our products must bear the signature of the PLEXICOAT AMERICA Technical Manager. This information and all further technical advice are based on PLEXICOAT AMERICA'S present knowledge and experience. However, PLEXICOAT AMERICA assumes no liability for providing such information and advice including the extent to which such information and advice may relate to existing third party intellectual property rights, especially patent rights. In particular, PLEXICOAT AMERICA disclaims all CONDITIONS AND WARRANTIES, WHETHER EXPRESS OR IMPLIED, INCLUDING THE IMPLIED WARRANTIES OF FITNESS FOR A PARTICULAR PURPOSE OR MERCHANTABILITY. PLEXICOAT AMERICA SHALL NOT BE RESPONSIBLE FOR CONSEQUENTIAL, INDIRECT OR INCIDENTAL DAMAGES (INCLUDING LOSS OF PROFITS) OF ANY KIND. PLEXICOAT AMERICA reserves the right to make any changes according to technological progress or further developments. It is the customer's responsibility and obligation to carefully inspect and test any incoming goods. Performance of the product(s) described herein should be verified by testing and carried out only by qualified experts. It is the sole responsibility of the customer to carry out and arrange for any such testing. Reference to trade names used by other companies is neither a recommendation, nor an endorsement of any product and does not imply that similar products could not be used.



Contact your local **PPG Protective and Marine Coatings Representative** or call

Plexicoat America, LLC

P O Box 65279 Baltimore, MD 21209 800-950-8172

www.plexicoat.com